

PRODUCT BULLETIN
GYPSUM PRODUCTS

PEBBLE GYPSUM
(FEED TO RAYMOND MILLS)

BULLETIN NO: R-2
DATE: 1/15/69
PAGE: 1 of 1
CANCELS: R-2
DATE: 10/6/64

OPERATING SPECIFICATIONS

Long Beach, Antioch, Seattle

Produced from San Marcos rock by crushing through Pennsylvania Swing Hammer Mills or equivalent.

Jacksonville, Delanco

Rock from the stockpile shall be blended with a bulldozer or skip loader to prevent feeding of all fine or all coarse rock to the crusher. Pebble gypsum is produced from Halifax, Nova Scotia rock by crushing through a Pennsylvania Swing Hammer Mill or equivalent after drying and screening operations. Rock feed to the mill shall be dried to 1.0% maximum free water with a rotary drier and shall be screened over a double deck vibrating screen with 2" and 7/8" size openings. Plus 2" rock is fed to the crusher. Minus 7/8" rock is fed to the pebble gypsum feed bins.

PRODUCT SPECIFICATIONS

	<u>Long Beach, Antioch Seattle</u>	<u>Delanco Jacksonville</u>
Purity (as $\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$)	95-98%	86-92%
Size grading	All through 1"	All through 1"
C1 Content of minus 50 mesh fines screened from pebble gypsum.	0.02% max.	0.05%

REQUIRED TESTS

When indicated by visual appearance or change in normal rock quality.